

# AQUAMAT-MONOELASTIC

## Highly flexible, fiber-reinforced, waterproofing cement-based slurry

### Description

AQUAMAT-MONOELASTIC is a one-component, highly flexible, waterproofing slurry consisting of a cement-based powder mortar enriched with resins. After hardening, it forms a seamless, jointless membrane with the following advantages:

- Crack-bridging ability.
- Total waterproofing against positive hydrostatic pressure up to 5 atm according to EN 12390-8. It can also withstand negative pressure.
- Protection of concrete from carbonation.
- No corrosive effect on the reinforcing steel in concrete.
- Vapor permeability.
- Resistance to aging.
- Bonding to wet surfaces without priming.
- Simple and low cost application.

Certified according to EN 1504-2 and classified as a coating for surface protection of concrete. CE marked. Certificate No.: 2032-CPR-10.11  
Also certified as root resistant according to UNE CEN/TS 14416 EX: 2014.

### Fields of application

It is used for waterproofing surfaces made of concrete, plaster, bricks, cement blocks, terrazzo, gypsum boards, wood, metal, etc. Ideal in cases where high flexibility and good adhesion of the waterproofing layer are required. Suitable for waterproofing substrates subject to expansion-contraction or vibration and show or are expected to show hairline cracks, such as terraces, balconies, above ground level water tanks, swimming pools, inverted roofs, etc. Ideal for application on terraces, rooftops, balconies and wet areas to be covered with tiles (bathrooms, kitchens). It can also be used for waterproofing basements, internally or externally, against moisture or water under pressure.

### Technical data

Basis:	cementitious powder
Color:	grey, white
Mixing ratio with water:	
• Application with a brush:	5.0-5.4 l/18 kg bag
• Application with a trowel:	4.1-4.5 l/18 kg bag
Mixing time:	3 min
Bulk density of dry mortar:	1.10 ± 0.05 kg/l
Bulk density of fresh mortar:	1.50 ± 0.10 kg/l
Adhesion (EN 1542):	≥ 1.0 N/mm <sup>2</sup>
Adhesion in combination with tiles (EN 1348):	> 0.5 N/mm <sup>2</sup>
Permeability to CO <sub>2</sub> : (EN 1062-6 Method A, requirement: Sd > 50m)	160 m
Capillary absorption and permeability to water: (EN 1062-3, requirement of EN 1504-2: w < 0.1)	0.03 kg/m <sup>2</sup> h <sup>0.5</sup>
Water vapor permeability: (EN ISO 7782-2, Class I < 5m)	Sd = 0.83 m
Pot life:	60 min at +20°C
Water penetration under positive hydrostatic pressure: (EN 12390-8, 3 days at 5 bar)	no penetration
Water penetration under negative hydrostatic pressure: (at 1.5 bar)	no penetration
<u>Durability against:</u>	
• Rain:	after ~ 1 day
• Tile fixing:	after ~ 1 day
• Water under pressure:	after ~. 7 days
• Backfill:	after ~ 3 days

# AQUAMAT-MONOELASTIC

## Directions for use

### 1. Substrate preparation

- The substrate must be clean, free of oily residue, loose material, dust, etc.
- Water leaks should be plugged with AQUAFIX ultra rapid-setting, cementitious leak-plugging mortar.
- Any cavities on concrete surface should be filled and smoothed out with DUROCRET, DUROCRET-FAST, RAPICRET or a cement mortar improved with ADIPLAST, after all loose aggregate has been removed and the surface has been well dampened.
- Starter bars and spacers should be cut to a depth of about 3 cm into the concrete and the holes should be sealed, as described above.
- Existing construction joints are opened longwise in a V shape to a depth of about 3 cm and are subsequently filled as above.
- Corners, like wall-floor junctions, should be filled and smoothly rounded with DUROCRET or a cement mortar improved with ADIPLAST (formation of a fillet, triangular in cross section, with sides of 5-6 cm).
- In case of masonry walls, joints should be first filled carefully, otherwise it is recommended to apply a cement mortar layer first improved with ADIPLAST.
- For waterproofing basements in old buildings, any existing plaster coat should be removed to a height of at least 50 cm above water level, before proceeding as above.
- Wherever flat surface formation is required (smoothing, slope creation, etc.) the use of DUROCRET, DUROCRET-FAST, RAPICRET or a mortar improved with ADIPLAST is recommended.

### 2. Application

The material is applied by brush or trowel in two or more layers, depending on the water load. The whole content of the 18 kg bag is added to the 5.0-5.4 l of water for application with a brush, or to 4.1-4.5 l of water for application with a trowel, under continuous stirring, until a uniform, viscous mixture is formed, suitable for brush application. The entire surface of the substrate should be well dampened but without ponding water.

Each new coating is applied after the previous one has dried. The freshly coated surface should be protected from high temperatures, rain and frost. In case AQUAMAT-MONOELASTIC needs to be locally reinforced (inside corners where forming fillets is not necessary, at junctions, etc.), the use of a 10 cm wide polyester fleece (30 g/m<sup>2</sup>) or fiberglass mesh (65 g/m<sup>2</sup>) is recommended.

## Consumption

Depending on the water load, the material is applied in 2-4 layers. Layers thicker than 1 mm should be avoided because the material may crack. Consumption: 1.4 kg/m<sup>2</sup>/mm.

## Packaging

18 kg bags.

## Shelf life – Storage

12 months from production date if stored in original, sealed packaging in dry, frost-free place.

## Remarks

- In case of water under pressure, care should be taken so that pumping, which keeps the water level low, does not stop before AQUAMAT-MONOELASTIC has sufficiently hardened. About 7 days are needed.
- In case of water under pressure, the structure bearing the waterproofing layer (wall, floor, etc.) should have been properly designed in order to be sufficiently static to withstand hydrostatic pressure.
- Temperature during application should be between +5°C and +35°C.
- Tiles should be fixed with a high performance tile adhesive like ISOMAT AK 20, ISOMAT AK 22, ISOMAT AK 25, ISOMAT AK-ELASTIC and ISOMAT AK-MEGARAPID.
- Due to cement content, AQUAMAT-MONOELASTIC reacts with water forming alkaline solutions, thus is classified as irritant.
- Consult the directions for safe use and precautions written on the packaging before use.

# AQUAMAT-MONOELASTIC

## AQUAMAT-MONOELASTIC GREY

 2032
<b>ISOMAT S.A.</b> 17 <sup>th</sup> km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece <b>12</b>
2032-CPR-10.11 DoP No.: AQUAMAT-MONOELASTIC GREY / 1608-03 <b>EN 1504-2</b> Surface protection products Coating Permeability to CO <sub>2</sub> : Sd > 50m Water vapor permeability: Class I (permeable) Capillary absorption: $w < 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}$ Adhesion: $\geq 1.0 \text{ N/mm}^2$ Reaction to fire: Euroclass F Dangerous substances comply with 5.3

## AQUAMAT-MONOELASTIC WHITE

 2032
<b>ISOMAT S.A.</b> 17 <sup>th</sup> km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece <b>17</b>
2032-CPR-10.11 DoP No.: AQUAMAT-MONOELASTIC WHITE / 1647-01 <b>EN 1504-2</b> Surface protection products Coating Permeability to CO <sub>2</sub> : Sd > 50m Water vapor permeability: Class I (permeable) Capillary absorption: $w < 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}$ Adhesion: $\geq 1.0 \text{ N/mm}^2$ Reaction to fire: Euroclass F Dangerous substances comply with 5.3

**ISOMAT S.A.**  
 BUILDING CHEMICALS AND MORTARS  
**MAIN OFFICES - FACTORY:**  
 17th km Thessaloniki - Ag. Athanasios Road,  
 P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,  
 Tel.: +30 2310 576 000, Fax: +30 2310 722 475  
[www.isomat.eu](http://www.isomat.eu) e-mail: [support@isomat.eu](mailto:support@isomat.eu)